

**CLEAN VERSION OF AMENDED CLAIMS**

Cancel claims 33 and 36-38.

Amend claims 24, 25, 27-29 and 35 as follows:

RECEIVED  
SEP 14 2007  
TC 1700

24. (amended) A laminated sheet or film comprising the following (co)extruded layers:

a substrate layer comprising - based on the sum of the amounts of the following components A and B and, if used, C and/or D, which totals 100% by weight -

1 - 99% by weight component A, which is of a graft copolymer of

1 - 99% by weight of a particulate graft base A1 comprising the following monomers:

80 - 99.99% by weight of at least one C<sub>1-8</sub>-alkyl ester of acrylic acid as component A11;

0.01 - 20% by weight of at least one polyfunctional crosslinking monomer as component A12;

1 - 99% by weight of a graft A2 comprising the following monomers, based on A2:

40 - 100% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component A21 and

up to 60% by weight of units of acrylonitrile or methacrylonitrile as component A22;

Sub F1

the graft A2 comprising at least one graft shell and the graft copolymer having a mean particle size of 50 - 1000 nm;

1 - 99% by weight of component B, which is a copolymer of

40 - 100% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component B1, and

up to 60% by weight of acrylonitrile or methacrylonitrile as component B2;

0 - 80% by weight of component C, which is a polycarbonate; and

0 - 50% by weight of component D, which is a fibrous or particulate filler or mixtures thereof;

and

a transparent top layer of polymethyl methacrylate.

25. (amended) A laminated sheet or film as defined in claim 24, additionally comprising between the top layer and the substrate layer

an (co)extruded interlayer of impact-modified polymethyl methacrylate,

polycarbonate or a molding composition of the substrate layer as set forth in

claim 24 without polycarbonate, if the substrate layer contains polycarbonate.

27. (amended) A laminated film comprising, in this order, the following

(co)extruded layers:

a substrate layer comprising a member selected from the group consisting of components A and B, and optionally C and D, as set forth in claim 24; ABS;

E 2  
polycarbonate; polybutylene terephthalate; polyethylene terephthalate;  
polyamide; polyetherimide; polyether ketone; polyphenylene sulfide; and  
polyphenylene ether or blends thereof, the substrate layer having a layer  
thickness of from 90 to 990  $\mu\text{m}$ ; and

a transparent top layer comprising a member selected from the group consisting  
of: polymethyl methacrylate; high-impact polymethyl methacrylate; ABS;  
polycarbonate; polyethylene terephthalate; styrene-acrylonitrile copolymers;  
polyamide; and polyether sulfone or polysulfone; the top layer having a layer  
thickness of from 10 to 100  $\mu\text{m}$ .

the substrate layer comprising special-effect colorants if the substrate layer and  
the top layer are composed of polyamide, the overall thickness of the laminated  
film being from 100 to 1000  $\mu\text{m}$ .

28. (amended) A laminated film as defined in claim 27, additionally comprising  
between the top layer and the substrate layer

an (co)extruded interlayer of a member selected from the group consisting of:  
polymethyl methacrylate; high-impact polymethyl methacrylate; ABS;  
polycarbonate; polyethylene terephthalate; styrene-acrylonitrile copolymers;  
polyamide; polyether sulfone or polysulfone, the interlayer comprising special-  
effect colorants and having a layer thickness of from 50 to 400  $\mu\text{m}$ .

29. (amended) A laminated film as defined in claim 28, additionally comprising,

E2  
could on the outer surface of the substrate layer,

an (co)extruded adhesion layer comprising an adhesion promoter and having a layer thickness of from 5 to 100  $\mu\text{m}$ .

E3 35. (amended) A laminated sheet or film as defined in claim 24, wherein a transport protection film is applied to the outside of the top layer.

Add new claims 39 and 40 as follows:

E4 39. (new) A laminated film comprising the following (co)extruded layers:  
a substrate layer comprising - based on the sum of the amounts of the following components A and B and, if used, C and/or D, which totals 100% by weight -

1 - 99% by weight component A, which is of a graft copolymer of

1 - 99% by weight of a particulate graft base A1 comprising the following monomers:

80 - 99.99% by weight of at least one  $\text{C}_{1-8}$ -alkyl ester of acrylic acid as component A11;

0.01 - 20% by weight of at least one polyfunctional crosslinking monomer as component A12;

1 - 99% by weight of a graft A2 comprising the following monomers, based on A2:

40 - 100% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component A21 and

up to 60% by weight of units of acrylonitrile or methacrylonitrile as component A22;

the graft A2 comprising at least one graft shell and the graft copolymer having a mean particle size of 50 - 1000 nm;

1 - 99% by weight of component B, which is a copolymer of

40 - 100% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component B1, and

up to 60% by weight of acrylonitrile or methacrylonitrile as component B2;

0 - 80% by weight of component C, which is a polycarbonate; and

0 - 50% by weight of component D, which is a fibrous or particulate filler or mixtures thereof;

and

a transparent top layer of polymethyl methacrylate.

40. (new) A laminated sheet or film, which is suitable for producing moldings, comprising the following (co)extruded layers:

a substrate layer comprising - based on the sum of the amounts of the following components A and B and, if used, C and/or D, which totals 100% by weight -

1 - 99% by weight component A, which is of a graft copolymer of

1 - 99% by weight of a particulate graft base A1 comprising the following monomers:

E4  
80 - 99.99% by weight of at least one C<sub>1-8</sub>-alkyl ester of acrylic acid  
as component A11;

0.01 - 20% by weight of at least one polyfunctional crosslinking  
monomer as component A12;

1 - 99% by weight of a graft A2 comprising the following monomers,  
based on A2:

40 - 100% by weight of units of styrene, a substituted styrene or a  
(meth)acrylate, or mixtures thereof, as component A21 and

up to 60% by weight of units of acrylonitrile or methacrylonitrile as  
component A22;

the graft A2 comprising at least one graft shell and the graft  
copolymer having a mean particle size of 50 - 1000 nm;

1 - 99% by weight of component B, which is a copolymer of

40 - 100% by weight of units of styrene, a substituted styrene or a  
(meth)acrylate, or mixtures thereof, as component B1, and

up to 60% by weight of acrylonitrile or methacrylonitrile as component B2;

0 - 80% by weight of component C, which is a polycarbonate; and

0 - 50% by weight of component D, which is a fibrous or particulate filler or  
mixtures thereof;

and

E4  
cont

a transparent top layer of polymethyl methacrylate.